



Europäisches
Patentamt

European
Patent Office

Office européen
des brevets

0 / 539961
17 JUN 2005

REC'D 16 FEB 2004

WIPO PCT

Bescheinigung

Certificate

Attestation

Die angehefteten Unterla-
gen stimmen mit der
ursprünglich eingereichten
Fassung der auf dem näch-
sten Blatt bezeichneten
europäischen Patentanmel-
dung überein.

The attached documents
are exact copies of the
European patent application
described on the following
page, as originally filed.

Les documents fixés à
cette attestation sont
conformes à la version
initialement déposée de
la demande de brevet
européen spécifiée à la
page suivante.

Patentanmeldung Nr. Patent application No. Demande de brevet n°

03250046.4

PCT/US03/41607

PRIORITY DOCUMENT
SUBMITTED OR TRANSMITTED IN
COMPLIANCE WITH
RULE 17.1(a) OR (b)

Der Präsident des Europäischen Patentamts;
Im Auftrag

For the President of the European Patent Office

Le Président de l'Office européen des brevets
p.o.

R C van Dijk



Anmeldung Nr:
Application no.: 03250046.4
Demande no:

Anmeldetag:
Date of filing: 03.01.03
Date de dépôt:

Anmelder/Applicant(s)/Demandeur(s):

DOW GLOBAL TECHNOLOGIES INC.
Washington Street, 1790 Building
Midland, Michigan 48674
ETATS-UNIS D'AMERIQUE

Bezeichnung der Erfindung/Title of the invention/Titre de l'invention:
(Falls die Bezeichnung der Erfindung nicht angegeben ist, siehe Beschreibung.
If no title is shown please refer to the description.
Si aucun titre n'est indiqué se référer à la description.)

Polyol composition and polyisocyanate-based foam prepared therefrom

In Anspruch genommene Priorität(en) / Priority(ies) claimed / Priorité(s)
revendiquée(s)
Staat/Tag/Aktenzeichen/State/Date/File no./Pays/Date/Numéro de dépôt:

Internationale Patentklassifikation/International Patent Classification/
Classification internationale des brevets:

C08G18/00

Am Anmeldetag benannte Vertragsstaaten/Contracting states designated at date of
filing/Etats contractants désignées lors du dépôt:

AT BE BG CH CY CZ DE DK EE ES FI FR GB GR HU IE IT LU MC NL
PT SE SI SK TR LI

Polyol Composition and
Polyisocyanate-based foam prepared therefrom

5

FIELD OF THE INVENTION

The present invention relates to a process for preparing polyisocyanurate foam, and also to a polyol composition, having utility in the preparation of polyisocyanate-based foam.

10

BACKGROUND OF THE INVENTION

Polyurethane and polyisocyanurate foam is being subjected to continuously changing and ever greater demands with respect to flame retardant and reduced smoke generation traits. It is also required that such foams are manufactured by processes that minimizes the use of blowing agents viewed as being harmful to the environment. Legislation has restricted the use of many substances traditionally used as physical blowing agent when preparing foam, and over the recent years there has been an emergence of alternative physical blowing agents including hydrocarbons, notably pentanes, and hydrofluoroalkanes such as for example tetrafluoroethane (R-134a) and pentafluoropropane (R-245fa).

There have also been many developments in the use of chemical blowing agents such as water and carbamates. Water is an attractive agent from the point of view of availability and economics. However, one of its disadvantages is the high consumption of isocyanate and high process temperatures associated with its use. Also in the case of polyisocyanurate foam, excessive amounts of water can be detrimental to foam properties leading to for example, high foam friability. An alternative to water is formic acid, which does not bring with it the same disadvantages. Formic acid reacts with isocyanate generating carbon monoxide and carbon dioxide gases that function as the blowing means.

The literature contains a number of publications that disclose the use of formic acid as blowing agent when preparing polyisocyanate-based foams such as polyurethane or polyisocyanurate foams.

5

US Patent 4,417,002 discloses the use of formic acid in combination with water as blowing agent for the manufacture of polyurethane foams.

10 US Patent 5,143,945 discloses the preparation of rigid polyurethane-polyisocyanurate foams in the presence of a blowing agent comprising a halocarbon in combination with an organic carboxylic acid, and optionally water. The carboxylic acid can be formic acid.

15 US Patent 5,286,758 discloses the use of formic acid and formate salts to prepare a low density rigid polyurethane under conditions of improved reactivity control.

20 US Patent 5,214,076 teaches the preparation of a carbodiimide-isocyanurate open celled foam from aromatic polyester polyols or aromatic amine polyols (ethoxylated TDA) in the presence of a blowing agent that can comprise formic acid.

US Patents 5,478,494 and 5,770,635 teach a polyol composition comprising a mixture of polyether polyols of differing equivalent weights and use of such composition in the presence of formic acid to prepare rigid polyurethane foams.

25 US Patent 5,762,822 teaches the manufacture of rigid polyurethane foam from a froth foaming mixture that employs as blowing agent a C1-C4 hydrofluorocarbon having a boiling point of 300K or less in combination with at least 2 weight percent of formic acid or salts thereof. Similar teachings are also presented in US Patent 5,883,146.

30 Despite this apparently extensive knowledge relating to formic acid as blowing agent when manufacturing polyurethane or polyisocyanurate foam there is still a need to

provide a foam that exhibits improved flame retardant performance or exhibits a reduced potential for smoke generation when burnt. Additionally for polyisocyanurate foam, the challenge is to combine above mentioned foam combustibility characteristics with convenient processing and generally acceptable foam mechanical properties .

5

SUMMARY OF THE INVENTION

It has now been discovered that formic acid-blown polyisocyanate-based foam prepared in the presence of an aromatic polyether polyol enables the production of foam with unexpected improvements in general physical performance including flame
10 retardancy and smoke reduction.

In one aspect, this invention is a polyol composition suitable for the preparation of a rigid polyisocyanate-based foam, containing one or more polyether or polyester polyols and a blowing agent, wherein; (a) the blowing agent comprises formic acid; and (b) the polyol comprises an aromatic polyoxyalkylene polyol based on an initiator obtained from
15 the condensation of a phenol with an aldehyde.

In a second aspect, this invention is a multi component system suitable for the preparation of a rigid polyisocyanate-based foam which comprises as first component an aromatic polyisocyanate, and as second component the polyol composition as mentioned above.

20 In a third aspect, this invention is a process for preparing a polyisocyanate-based foam which comprises bringing together under foam-forming conditions a polyisocyanate with the polyol composition as described above.

In a fourth and fifth aspect, this invention is a polyurethane foam, or a polyisocyanurate foam, obtained by bringing together under foam-forming conditions a
25 polyisocyanate with a polyol composition characterized in that:

- a) the polyisocyanate is present in an amount to provide for an isocyanate reaction index of from about 80 to about 150 (for polyurethane) or from about 150 to about 600 (for polyisocyanurate); and

b) the polyol composition comprises (i) formic acid; and (ii) an aromatic polyoxyalkylene polyol based on an initiator obtained from the condensation of a phenol with an aldehyde.

In a sixth aspect, this invention is a process for preparing a closed-celled polyisocyanurate foam by bringing into contact under foam-forming conditions a polyisocyanate with a polyol composition in the presence of a blowing agent mixture wherein the polyol composition comprises an aromatic polyester polyol and an aromatic polyether polyol; and wherein the blowing agent mixture comprises formic acid and an additional blowing agent, which is a hydrofluoroalkane selected from the group consisting of tetrafluoroethane, pentafluoropropane, heptafluoropropane and pentafluorobutane, or a hydrocarbon selected from the group consisting of butane, pentane, cyclopentane, hexane, cyclohexane, and heptane, and the isomers thereof, and wherein the polyisocyanate is present in an amount to provide for an isocyanate reaction index of from greater than 150 to about 600.

In a seventh aspect, this invention is a laminate comprising the above-mentioned polyurethane or polyisocyanurate foam.

DETAILED DESCRIPTION OF THE INVENTION

The rigid polyisocyanate-based foams in accordance with this invention are prepared by bringing together under foam-forming conditions a polyisocyanate with a particular polyol composition comprising an aromatic polyol and a blowing agent comprising formic acid. The aromatic polyol is an aromatic polyether polyol or a combination thereof with an aromatic polyester polyol. The preferred aromatic polyether polyols are the aromatic polyoxyalkylene polyols based on an initiator derived from the condensation of a phenol with an aldehyde. In a preferred embodiment of this invention, the aromatic polyoxyalkylene polyol used is one obtained by reacting a condensate adduct of phenol and formaldehyde, with one or more alkylene oxides including ethylene oxide, propylene oxide, and butylene oxide. Such polyols, sometimes referred to as "Novolak" initiated polyols are known to one of skill in the art, and can be obtained by methods such as disclosed in, for example, US Patents Nos. 2,838,473; 2,938,884;

3,470,118; 3,686,101 and 4,046,721. Typically, "Novolak" starting materials are prepared by reacting a phenol (for example a cresol) with from about 0.8 to 1.5 moles of formaldehyde per mole of the phenol in the presence of an acidic catalyst to form a polynuclear condensation product containing from about 2.1 to 12, preferably from about 2.2 to 6, and more preferably from about 3 to about 5 phenol units/molecule. The novolak resin is then reacted with an alkylene oxide such as ethylene oxide, propylene oxide, butylene oxide, or isobutylene oxide, to form an oxyalkylated product containing a plurality of hydroxyl groups. For the purpose of the present invention, preferred "Novolak" polyols are those having an average of from about 3 to about 6 hydroxyl moieties per molecule and an average hydroxyl equivalent weight of from about 100 to about 500, preferably from about 100 to about 300. The "Novolak" initiated polyether polyol preferably constitutes from about 1, more preferably from about 10, more preferably from about 20, and yet more preferably from about 25; and up to about 99, preferably to about 70, more preferably up to about 60 parts by weight of the total weight of polyol composition.

The polyol composition comprises the formic acid in an amount to provide foam of the desired density. Typically the formic acid is present in an amount of from 0.5 to 8 parts, and more typically from about 1.5 to about 6 parts by weight per 100 parts by weight of the polyol composition including the formic acid. While formic acid is the carboxylic acid of preference, it is also contemplated that minor amounts of other aliphatic mono and polycarboxylic acids may also be employed, such as those disclosed in US Patent 5,143,945 column 3, lines – column 4, line 28, incorporated herein by reference, and including isobutyric acid, ethylbutyric acid, and ethylhexanoic acid.

In addition to the "Novolak" polyol and formic acid, the polyol composition may contain other polyether and polyester polyols along with additional blowing agents, (for example water), catalysts, surfactants, fillers and Flame Retardant additives as commonly used in the manufacture of polyisocyanate-based foams.

Examples of additional blowing agents which can be present include

hydrochlorofluorocarbons, hydrofluorocarbons and hydrocarbons, as well as water. The additional blowing agent is preferably used in an amount of from 2 to 15 parts preferably from 4 to 10 parts, per 100 parts by weight of the polyol composition. Suitable

5 hydrofluoroalkanes are the C₁-C₄ compounds including difluoromethane (R-32), 1,1,1,2-tetrafluoroethane (R-134a), 1,1-difluoroethane (R-152a), difluorochloroethane (R-142b), trifluoromethane (R-23), heptafluoropropane (R-227a), hexafluoropropane (R-136), 1,1,1-trifluoroethane (R-133), fluoroethane (R-161), 1,1,1,2,2-pentafluoropropane (R-245fa), pentafluoropropylene (R-2125a), 1,1,1,3-tetrafluoropropane, tetrafluoropropylene (R-

10 2134a), 1,1,2,3,3-pentafluoropropane and 1,1,1,3,3-pentafluoro-n-butane. When a hydrofluorocarbon blowing agent is present, preferred is tetrafluoroethane (R-134a), pentafluoropropane (R-245fa) or pentafluorobutane (R-365). Suitable hydrocarbons for use as blowing agent include nonhalogenated hydrocarbons such as butane, isobutane, 2,3-dimethylbutane, n- and i-pentane isomers, hexane isomers, heptane isomers and

15 cycloalkanes including cyclopentane, cyclohexane and cycloheptane. Preferred hydrocarbons for use as blowing agent include cyclopentane and notably n-pentane and iso-pentane. In a preferred embodiment of this invention the polyol composition comprises a physical blowing agent selected from the group consisting of

20 tetrafluoroethane (R-134a), pentafluoropropane (R-245fa), pentafluorobutane (R-365), cyclopentane, n-pentane and iso-pentane. Water may also be present in the polyol composition added intentionally as a blowing agent. When intending to prepare polyurethane foam advantageously water is present in an amount of from about 0.5 to about 10 parts, and preferably from about 1 to about 6 parts, per 100 parts by weight of the polyol composition. When intending to prepare a polyisocyanurate foam, in order to

25 obtain facilitate and give desirable processing characteristics, it is advantageous not to exceed 2 parts of water, and preferably not to exceed 1.5 parts of water; and even to have water absent.

Other polyols which may be present in the polyol composition include one or

30 more other polyether or polyesters polyols of the kind typically employed in processes to make polyurethane foam. Other compounds having at least two isocyanate reactive

hydrogen atoms may also be present, for example polythioether polyols, polyester amides and polyacetals containing hydroxyl groups, aliphatic polycarbonates containing hydroxyl groups, amine terminated polyoxyalkylene polyethers, and preferably, polyester polyols, polyoxyalkylene polyether polyols, and graft dispersion polyols. Mixtures of two
5 or more of the aforesaid materials may also be employed.

The term "polyester polyol" as used in this specification and claims includes any minor amounts of unreacted polyol remaining after the preparation of the polyester polyol and/or unesterified polyol (e.g., glycol) added after the preparation of the polyester
10 polyol. Suitable polyester polyols can be produced, for example, from organic dicarboxylic acids with 2 to 12 carbons, preferably aliphatic dicarboxylic acids with 4 to 6 carbons, and multivalent alcohols, preferably diols, with 2 to 12 carbons, preferably 2 to 6 carbons. Examples of dicarboxylic acids include succinic acid, glutaric acid, adipic acid, suberic acid, azelaic acid, sebacic acid, decanedicarboxylic acid, maleic acid,
15 fumaric acid, phthalic acid, isophthalic acid, and terephthalic acid. The dicarboxylic acids can be used individually or in mixtures. Instead of the free dicarboxylic acids, the corresponding dicarboxylic acid derivatives may also be used such as dicarboxylic acid mono- or di- esters of alcohols with 1 to 4 carbons, or dicarboxylic acid anhydrides. Dicarboxylic acid mixtures of succinic acid, glutaric acid and adipic acid in quantity
20 ratios of 20:35:35- 50:20- 32 parts by weight are preferred, especially adipic acid. Examples of divalent and multivalent alcohols, especially diols, include ethanediol, diethylene glycol, 1,2- and 1,3-propanediol, dipropylene glycol, 1, 4- butanediol, 1,5- pentanediol, 1,6-hexanediol, 1,10-decanediol, glycerine and trimethylolpropanes, tripropylene glycol, tetraethylene glycol, tetrapropylene glycol, tetramethylene glycol,
25 1,4-cyclohexane- dimethanol, ethanediol, diethylene glycol, 1,4-butanediol, 1,5- pentanediol, 1,6- hexanediol, or mixtures of at least two of these diols are preferred, especially mixtures of 1,4-butanediol, 1,5-pentanediol, and 1,6- hexanediol. Furthermore, polyester polyols of lactones, e.g., . epsilon.- caprolactone or hydroxycarboxylic acids, e.g., . omega.- hydroxycaproic acid, may also be used. While the aromatic polyester
30 polyols can be prepared from substantially pure reactant materials, more complex ingredients are advantageously used, such as the side stream, waste or scrap residues

from the manufacture of phthalic acid, terephthalic acid, dimethyl terephthalate, polyethylene terephthalate, and the like. Other residues are DMT process residues, which are waste or scrap residues from the manufacture of dimethyl terephthalate (DMT). The present applicants have observed that for certain applications it is particularly advantageous for reasons of foam performance and processing to have present in the polyol composition both the "Novolak" polyol and an additional aromatic polyol which can be an aromatic polyether or aromatic polyester polyol.

Polyether polyols that additionally may be present include those which can be obtained by known methods. For example, polyether polyols can be produced by anionic polymerization with alkali hydroxides such as sodium hydroxide or potassium hydroxide or alkali alcoholates, such as sodium methylate, sodium ethylate, or potassium ethylate or potassium isopropylate as catalysts and with the addition of at least one initiator molecule containing 2 to 8, preferably 3 to 8, reactive hydrogens or by cationic polymerization with Lewis acids such as antimony pentachloride, boron trifluoride etherate, etc., or bleaching earth as catalysts from one or more alkylene oxides with 2 to 4 carbons in the alkylene radical. Any suitable alkylene oxide may be used such as 1,3-propylene oxide, 1,2- and 2,3-butylene oxide, amylene oxides, styrene oxide, and preferably ethylene oxide and 1,2-propylene oxide and mixtures of these oxides. The polyalkylene polyether polyols may be prepared from other starting materials such as tetrahydrofuran and alkylene oxide-tetrahydrofuran mixtures; epihalohydrins such as epichlorohydrin; as well as aralkylene oxides such as styrene oxide. The polyalkylene polyether polyols may have either primary or secondary hydroxyl groups, preferably secondary hydroxyl groups from the addition of propylene oxide onto an initiator because these groups are slower to react. Included among the polyether polyols are polyoxyethylene glycol, polyoxypropylene glycol, polyoxybutylene glycol, polytetramethylene glycol, block copolymers, for example, combinations of polyoxypropylene and polyoxyethylene glycols, poly-1,2-oxybutylene and polyoxyethylene glycols, poly-1,4-tetramethylene and polyoxyethylene glycols, and copolymer glycols prepared from blends or sequential addition of two or more alkylene oxides. The polyalkylene polyether polyols may be prepared by any known process such as, for example, the process disclosed by Wurtz in 1859 and

Encyclopedia of Chemical Technology, Vol. 7, pp. 257- 262, published by Interscience Publishers, Inc. (1951) or in U.S. Pat. No. 1,922,459. Polyethers which are preferred include the alkylene oxide addition products of polyhydric alcohols such as ethylene glycol, propylene glycol, dipropylene glycol, trimethylene glycol, 1,2- butanediol, 1,5-
5 pentanediol, 1,6-hexanediol, 1,7-heptanediol, hydroquinone, resorcinol glycerol, glycerine, 1,1,1-trimethylol- propane, 1,1,1-trimethylolethane, pentaerythritol, 1,2,6-hexanetriol, a- methyl glucoside, sucrose, and sorbitol. Also included within the term "polyhydric alcohol" are compounds derived from phenol such as 2,2- bis(4-
10 hydroxyphenyl)-propane, commonly known as Bisphenol A. Particularly preferred in the polyol composition is at least one polyol which is initiated with a compound having at least two primary or secondary amine groups, a polyhydric alcohol having 4 or more hydroxyl groups, such as sucrose, or a mixture of initiators employing a polyhydric alcohol having at least 4 hydroxyl groups and compounds having at least two primary or secondary amine groups. Suitable organic amine initiators which may be condensed
15 with alkylene oxides include aromatic amines such as aniline, N- alkylphenylene-diamines, 2,4'-, 2,2'-, and 4,4'-methylenedianiline, 2,6- or 2,4-toluenediamine, vicinal toluediamines, o-chloro-aniline, p- aminoaniline, 1,5-diaminonaphthalene, methylene dianiline, the various condensation products of aniline and formaldehyde, and the isomeric diaminotoluenes; and aliphatic amines such as mono-, di-, and trialkanolamines,
20 ethylene diamine, propylene diamine, diethylenetriamine, methylamine, triisopropanolamine, 1,3- diaminopropane, 1,3-diaminobutane, and 1,4-diaminobutane. Preferable amines include monoethanolamine, vicinal toluediamines, ethylenediamines, and propylenediamine. Yet another class of aromatic polyether polyols contemplated for use in this invention are the Mannich-based polyol an alkylene
25 oxide adduct of phenol/formaldehyde/alkanolamine resin, frequently called a "Mannich" polyol such as disclosed in U.S. Patents 4,883,826; 4,939,182; and 5,120,815.

When the blowing agent composition includes physical blowing agents such as, for example, HFC245fa, HFC134a or HFC365mfc, the combination of an aromatic
30 polyester polyol and an aromatic polyether polyols is particularly preferred in order to

achieve desirable flame retardant and smoke suppressant characteristics together with attractive storage stability of the polyol composition and convenient foam processing.

5 In the practice of the present invention, the applicants have observed that for the purpose of enhancing foam integrity and improving surface adhesion it is advantageous to incorporated small amounts of high equivalent weight polyether polyols such as are typically used in molded flexible polyurethanes, for example, VORANOL 1421 available from The Dow Chemical Company and understood to be a glycerine-initiated polyoxypropylene-oxyethylene polyol having a molecular weight of approximately 5100
10 and an oxyethylene content of approximately 70 percent.

In addition to the foregoing components, it is often desirable to have certain other ingredients present in the polyol composition for the purpose of facilitating the subsequent use in preparing cellular polymers. Among these additional ingredients are
15 catalysts, surfactants, preservatives, colorants, antioxidants, flame retardants, reinforcing agents, stabilizers and fillers. In making polyurethane foam, it is generally highly preferred to employ a minor amount of a surfactant to stabilize the foaming reaction mixture until it cures. Such surfactants advantageously comprise a liquid or solid organosilicone surfactant. Other, less preferred surfactants include polyethylene glycol
20 ethers of long-chain alcohols, tertiary amine or alkanolamine salts of long-chain alkyl acid sulfate esters, alkyl sulfonic esters and alkyl arylsulfonic acids. Such surfactants are employed in amounts sufficient to stabilize the foaming reaction mixture against collapse and the formation of large, uneven cells. Typically, 0.2 to 3 parts of the surfactant per 100 parts by weight polyol composition are sufficient for this purpose.

25 Such Flame retardants advantageously present include for example exfoliating graphite, phosphonate esters, phosphate esters, halogenated phosphate esters or a combination thereof. Phosphonate esters for use in the present invention can be represented by the formula $R-P(O)(OR')(OR'')$ where R, R' and R'' are each independently
30 an alkyl having 1 to 4 carbon atoms. Preferred members of this group are dimethyl methylphosphonate (DMMP) and diethyl ethyl phosphonate (DEEP). Phosphate esters

which can be used in the present invention are trialkyl phosphates, such as triethyl phosphate, and tricresyl phosphate. When used, the phosphonate or phosphate ester flame retardants are present in the final foam at a level of from 0.5 to 20 percent by weight of the final foam. Preferably they are 1 to 15 percent by weight of the final foam.

5 More preferably they constitute 2 to 10 percent by weight of the final foam.

Halogenated phosphate esters which are associated with fire retardation are known in the art and can be represented by the general formula $P(O)(OR'X'n)(OR''X''n)(OR'''X'''n)$, where R', R'' and R''' are each independently an alkyl having 1 to 4 carbon atoms, X', X'' and X''' are each independently a halogen and n is an integer from 1 to 3. Examples of

10 halogenated phosphate esters include 2-chloroethanol phosphate; 1-chloro-2-propanol phosphate [tris(1-chloro-2-propyl) phosphate] (TCPP); 1,3-dichloro-2-propanol Phosphate also called tris(1,3-dichloro-2-propyl) phosphate; tri(2-chloroethyl) phosphate; tri(2,2-dichloroisopropyl) phosphate; tri(2,3-dibromopropyl) phosphate; tri(1,3-dichloropropyl)phosphate; tetrakis(2-chloroethyl) ethylene diphosphate; bis(2-

15 chloroethyl) 2-chloroethylphosphonate; cliphosphates [2-chloroethyl diphosphate]; tetrakis(2-chloroethyl) ethylenediphosphate; tris-(2-chloroethyl)-phosphate, tris-(2-chloropropyl)phosphate, tris-(2,3-dibromopropyl)-phosphate, tris(1,3-dichloropropyl)phosphate tetrakis(2-chloroethyl-ethylene diphosphate and tetrakis(2-chloroethyl) ethyleneoxyethylenediphosphate. Tribromonopentyl chloroalkyl

20 phosphates as disclosed in EP 0 735 039 having the formula $[(BrCH_2)_3C-CH_2O]_n PO (OCYHCH_2Cl)_3$ -where Y represents a hydrogen, an alkyl having 1 to 3 carbon atoms, or chloroalkyl group and n is from 0.95 to 1.15 may also be used.

25 One or more catalysts for the reaction of the polyol (and water, if present) with the polyisocyanate are advantageously used. Any suitable urethane catalyst may be used, including tertiary amine compounds and organometallic compounds. Exemplary tertiary amine compounds include triethylenediamine, N-methylmorpholine, N,N-dimethylcyclohexylamine, pentamethyldiethylenetriamine, tetramethylethylenediamine,

30 1-methyl-4-dimethylaminoethylpiperazine, 3-methoxy-N-dimethylpropylamine, N-ethylmorpholine, diethylethanolamine, N-cocmorpholine, N,N-dimethyl-N',N'-dimethyl

isopropylpropylenediamine, N,N-diethyl-3-diethylaminopropylamine and dimethylbenzylamine. Exemplary organometallic catalysts include organomercury, organolead, organoferric and organotin catalysts, with organotin catalysts being preferred among these. Suitable tin catalysts include stannous chloride, tin salts of carboxylic acids
5 such as dibutyltin di-laurate, as well as other organometallic compounds such as are disclosed in U.S. Patent 2,846,408. A catalyst for the trimerization of polyisocyanates, resulting in a polyisocyanurate, such as an alkali metal alkoxide may also optionally be employed herein. Such catalysts are used in an amount which measurably increases the rate of polyurethane or polyisocyanurate formation. Typical amounts are 0.001 to 3 parts
10 of catalyst per 100 parts by weight of total polyol.

A polyisocyanate-based foam is obtained by bringing together the above described polyol composition under foaming forming conditions with a polyisocyanate. In this manner polyurethane or polyisocyanurate foam can be prepared. Polyisocyanates
15 useful in making the foam include aliphatic and cycloaliphatic and preferably aromatic polyisocyanates or combinations thereof, advantageously having an average of from 2 to 3.5, and preferably from 2.4 to 3.2 isocyanate groups per molecule. A crude polyisocyanate may also be used in the practice of this invention, such as crude toluene diisocyanate obtained by the phosgenation of a mixture of toluene diamine or the crude
20 diphenylmethane diisocyanate obtained by the phosgenation of crude methylene diphenylamine. The preferred polyisocyanates are aromatic polyisocyanates such as disclosed in U.S. Patent 3,215,652. Especially preferred are methylene-bridged polyphenyl polyisocyanates and mixtures thereof with crude diphenylmethane diisocyanate, due to their ability to cross-link the polyurethane.

25
For the preparation of a polyurethane foam the polyisocyanate is present in an amount, relative to the polyol composition, so as to provide an isocyanate reaction index of from about 80 to about 150, preferably from about 90 to about 130. An isocyanate index of 100 corresponds to one isocyanate equivalent per active hydrogen atom present
30 in the polyol composition. For the preparation of a polyisocyanurate foam the polyisocyanate is present in an amount to provide an isocyanate reaction index of from

about 150 to about 600, preferably from about 200 to about 500. The polyol composition of this invention is particularly useful in the preparation of polyisocyanurate foam.

5 In general, the rigid foams may be produced by discontinuous or continuous processes, including the process referred to generally as the discontinuous panel process (DCP) and continuous lamination, with the foaming reaction and subsequent curing being carried out in molds or on conveyors. When utilizing the foams in laminates, the facing may be flexible, for example, aluminum foil or coated paper, or may be a rigid material
10 such as plaster-board, polyester facing or steel facing. Other processes to prepare construction foams are known as spray and block foams.

 The rigid foam of the present invention are for the most part closed-cell foam. By closed-cells it is meant that at least 75 percent, preferably 80 percent or greater, and more
15 preferably 85 percent or more of the cells are closed. In a preferred embodiment, 90 percent or more of the cells are closed. Because of the closed-cell structures, the rigid polyurethanes of the present invention are useful for thermal insulation applications such as roofing, sheathing and in-situ spray applications.

20 The following examples are given to illustrate the invention and should not be interpreted as limiting it in any way. Unless stated otherwise, all parts and percentages are by weight. The following abbreviations identify various materials used in the Examples.

25 Polyol A: A "Novolak" polyol being a oxypropylene-oxyalkylene adduct based on a phenol-formaldehyde condensate having an average functionality of about 3.3. Polyol hydroxyl number is 196

 Polyol B A polyester polyol, TEROL 198 available from Oxid understood to have a
30 hydroxyl number 198 .

Polyol C . A glycerine-initiated oxypropylene-oxyethylene polyol, VORANOL 1421,
available from The Dow Chemical Company. Hydroxyl Number 35.

Polyol D A sucrose initiated oxypropylene-oxyethylene polyol, VORANOL 280,
5 available from The Dow Chemical Company . Hydroxyl Number 280

	DEEP	Diethyl ethylphosphonate
	TCPP	Trichloroisopropylphosphate
	MEG	ethylene glycol
10	DABCO DC5598	Surfactant, available from Air Products
	DABCO TMR	Catalyst, available from Air Products
	DABCO K15	Catalyst, available from Air Products
	PMDETA	pentamethyldiethylenetriamine
	DMCHA	dimethylcyclohexylamine
15	Toyocat DM70	Catalyst ,available from Tosoh
	Curithane 206	Catalyst available from The Dow Chemical Company
	Formic Acid	Purity 98 % , supplied by Incofar
	n-pentane	commercial grade as provided by Synthesis
	ISO A	VORANATE 600, A higher functionality crude diphenylmethane
20		diisocyanate available from The Dow Chemical Company
	ISO B	VORANATE 220, A standard grade crude diphenylmethane
		diisocyanate available from The Dow Chemical Company

Foam Examples 1-9

25 Foams 1 to 9 (2, 4 , 7 and 9 are comparative Foams) are prepared using a Cannon
A40 high pressure machine. Reactants and amounts are indicated in the following table.
Foams 1 – 4 have been evaluated in the production of metal-faced continuous laminate
panels. Foams 5 to 9 have been evaluated in the production of discontinuous panels.
Foams prepared in the presence of formic acid exhibit a notably stronger flame retardant
30 and smoke suppressant characteristics than those foams prepared in the absence of the
acid. Foams prepared in the presence of formic acid and pentane, provided both

surprisingly good flame retardant and reduced smoke generation traits; such performance in the presence of pentane had not been expected giving consideration to the normal flammable properties of pentane.

Comparative example Foam 9 show that use of a polyol composition comprising
5 uniquely an aromatic polyester polyol is unattractive with observation of poor skin curing, resulting in more difficult processing.

A further observation is that this invention provides for polyol compositions of attractive storage stability where such compositions includes as blowing agent,
10 HFC245fa (Foam 8).

Foam Example 10

A polyisocyanurate foam is prepared in a manner similar to Foams 1-9 with reactants as noted below. In this instance the polyol composition is a combination of an
15 aromatic polyester polyol and an aromatic polyether polyol with good blend stability in the presence of the blowing agent, pentafluoropropane (245fa).

47 pbw	TERATE 4026 , a polyester polyol from Kosa, OH value 205
7	Polyol C
20 10	TERACOL 5902, a TDA initiated, oxypropylene - oxyethylene polyol available from The Dow Chemical Company, OH value 375
5	DEEP
9	TCP
6	TEP surfactant
25 1.6	Surfactant
0.3	DMCHA
2.2	CURITHANE 206
0.3	water
2.6	formic acid
30 9.1	Hfc 245fa

Iso A (Index) 170 pbw /(300)

Reactivity (CT/GT) 4/44
35 Free rise density (kg/m3) 38.3

The foam is observed to have a Butler chimney flame spread of 15.5 cm; a weight retention of 93.4%; and a smoke development (NBS) of 59. Processing characteristics of

the foam are attractive with a 100% skin cure being noted in about 7 minutes at a mold temperature of 45C.

Pbw	Foam 1	Foam 2*	Foam 3	Foam 4*	Foam 5	Foam 6	Foam 7*	Foam 8	Foam 9*
Polyol A	30.1	30	31	31	52.3	45.4	51	24.8	
Polyol B	25	25	30.5	30.5	/	/	/	24.7	47.6 (*)
Polyol C	11.5	11.5	/	/	/	/	/		
Polyol D	/	/	9.1	9.1	/	/	/		
DEEP	11.5	11.4	9.8	9.8	8	12.9	11	8	12.89
TCPP	14	14	9.8	9.8	30	31.7	31.9	30	30.25
MEG	/	/	0.5	0.5	/	/	/		
L6900	/	/	/	/	/	1.98	1.5		
DABCO DC5598	1.8	1.8	2.95	2.95	3	/	/	3	3
DMCHA	0.47	0.4			0.2	/	/	0.05	
DMEE	/	/	/	/	/	0.2	/		
Toyocat DM70	0.2								
PMDETA	/	0.07	0.1	0.1	/	/	/		
CURITHANE 52	/	/	4.92	4.92	/	3.03	/		
Dabco K15	0.33								
CURITHANE 206	1.74	2.2	/	/	1.5	/	0.7	1.45	1.5
DABCO TMR	/	/	1.0	1.0	/	/	/		
Water	1.91	3.15	/	1.2	/	1.98	3.12		1.98
Formic Acid	1.45	/	1.6	/	4.99	2.78	/	4	2.78
HFC 245fa								4	
n-Pentane	/	/	9	9	/	/	/		
ISO A (Index)	188.5 (300)	231 (300)	180 (340)	180 (320)	/	/			
ISO B	/	/	/	/	160 (293)	168 (240)	180 (247)	143 (290)	179 (240)
Polyol blend stability	Clear ,stable	Clear ,stable	/		Clear ,stable	Clear ,stable	Clear ,stable	Clear ,stable	
Reactivity CT/GT (secs)	5 / 42	5 / 26	6 / 41		6 / 95	12 / 100	13 / 88	6/83	20/105
Free-Rise Core density (kg/m ³)	44.9	43.3	38.9		34	31	35	32.4	35
DIN 4102 B2 rating (cm)	5	/	6.5	9.2	6	9	12.5	6.4	7.8
Butler Chimney test									
Flame spread	15.9	20 cm	/						
Weight retention	cm 92.6 %	91.5	89.8	87					
Smoke development (NBS)									
	137	176	66	86					
% skin cure (45-50C mold)	>70%	25 % at	100%at	25% at	100%	100%	70% (soft	100%	50% (soft

temp)	at 7min	7 min	5 min	5 min	12 min	12 min	foam) 12'	12 min	foam) 12'
-------	---------	-------	-------	-------	--------	--------	-----------	--------	-----------

(*) Terate 2540, polyester polyol from Kosa , hydroxyl number 250

CLAIMS:

- 1) A polyol composition suitable for the preparation of a rigid polyisocyanate-based foam containing one or more polyether or polyester polyols and a blowing agent,
5 wherein;
 - a) the blowing agent comprises formic acid; and
 - b) the polyol comprises an aromatic polyoxyalkylene polyol based on an initiator obtained from the condensation of a phenol with an aldehyde.
- 2) The polyol composition of Claim 1 which additionally comprises a physical blowing
10 agent.
- 3) The polyol composition of Claim 2 wherein the physical blowing agent is a hydrocarbon selected from the group consisting of butane, pentane, cyclopentane, hexane, cyclohexane, and heptane, and the isomers thereof.
- 4) The polyol composition of Claim 2 wherein the physical blowing agent is a C₁-C₄
15 hydrofluoroalkane or hydrochlorofluoroalkane.
- 5) The polyol composition of Claim 4 wherein the physical blowing agent is a hydrofluoroalkane selected from the group consisting of difluoromethane, difluoroethane, tetrafluoroethane, pentafluoropropane and hexafluorobutane.
- 6) The polyol composition of Claim 1 where in the aromatic polyoxyalkylene polyol
20 based on an initiator obtained from the condensation of phenol with formaldehyde.
- 7) The polyol composition of Claim 6 wherein the aromatic polyoxyalkylene polyol is present in an amount of at least 20 weight percent based on total weight of the polyol composition.
- 8) The polyol composition of Claim 7 that further comprises an aromatic polyester
25 polyol.

- 9) A multi component system suitable for the preparation of rigid polyisocyanate-based foam that comprises as first component an aromatic polyisocyanate, and as second component a polyol composition as claimed in Claim 1.
- 10) A process for preparing a polyisocyanate-based foam which comprises bringing together under foam-forming conditions a polyisocyanate with a polyol composition as claimed in Claim 1.
- 11) The process of Claim 10 where in the polyisocyanate is present in an amount to provide for an isocyanate reaction index of from about 80 to about 150.
- 12) The process of Claim 10 where in the polyisocyanate is present in an amount to provide for an isocyanate reaction index of from about 150 to about 600.
- 13) A polyurethane foam obtained by bringing together under foam-forming conditions a polyisocyanate with a polyol composition characterized in that:
- a) the polyisocyanate is present in an amount to provide for an isocyanate reaction index of from about 80 to about 150; and
 - b) the polyol composition comprises (i) formic acid; and (ii) an aromatic polyoxyalkylene polyol based on an initiator obtained from the condensation of a phenol with an aldehyde.
- 14) A polyisocyanurate foam obtained by bringing together under foam-forming conditions a polyisocyanate with a polyol composition characterized in that:
- a) the polyisocyanate is present in an amount to provide for an isocyanate reaction index of from about 150 to about 600; and
 - b) the polyol composition comprises (i) formic acid; and (ii) an aromatic polyoxyalkylene polyol based on an initiator obtained from the condensation of a phenol with an aldehyde.
- 15) A laminate comprising the polyurethane foam of Claim 13 or Claim 14.

- 16) A process for preparing a closed-celled polyisocyanurate foam by bringing into contact under foam-forming conditions a polyisocyanate with a polyol composition in the presence of a blowing agent mixture wherein the polyol composition comprises an aromatic polyester polyol and an aromatic polyether polyol; and wherein the blowing agent mixture comprises formic acid and a hydrofluoroalkane selected from the group consisting of tetrafluoroethane, pentafluoropropane, heptafluoropropane and pentafluorobutane, and characterized in that the polyisocyanate is present in an amount to provide for an isocyanate reaction index of from greater than 150 to about 600.
- 17) The process of Claim 16 wherein water is present in an amount of from 0 to about 2 parts by weight per 100 parts of the combined weight of the polyol composition and blowing agent mixture.
- 18) The process of Claim 16 wherein the aromatic polyether polyol comprises a toluenediamine-initiated polyol, a Mannich base-initiated polyol, a methylene diphenylamine-initiated polyol, a phenol-acetone condensate-initiated polyol or a phenol-formaldehyde condensate-initiated polyol.
- 19) A process for preparing a closed-celled polyisocyanurate foam by bringing into contact under foam-forming conditions a polyisocyanate with a polyol composition in the presence of a blowing agent mixture wherein the polyol composition comprises an aromatic polyester polyol and an aromatic polyether polyol; and wherein the blowing agent mixture comprises formic acid and a hydrocarbon selected from the group consisting of butane, pentane, cyclopentane, hexane, cyclohexane, and heptane, and the isomers thereof and characterized in that the polyisocyanate is present in an amount to provide for an isocyanate reaction index of from greater than 150 to about 600.

Polyol Composition and
Polyisocyanate-based foam prepared therefrom

ABSTRACT OF THE DISCLOSURE

A polyol composition is disclosed that comprises an aromatic polyether polyol , preferably based on the condensation product of a phenol with an aldehyde and as blowing agent, formic acid. The polyol composition finds utility in the manufacture of polyurethane and particularly polyisocyanurate foams having attractive flame retardant
5 and reduced smoke generation characteristics.

**This Page is Inserted by IFW Indexing and Scanning
Operations and is not part of the Official Record**

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images include but are not limited to the items checked:

- ☒ **BLACK BORDERS**
- ☐ **IMAGE CUT OFF AT TOP, BOTTOM OR SIDES**
- ☐ **FADED TEXT OR DRAWING**
- ☐ **BLURRED OR ILLEGIBLE TEXT OR DRAWING**
- ☐ **SKEWED/SLANTED IMAGES**
- ☐ **COLOR OR BLACK AND WHITE PHOTOGRAPHS**
- ☐ **GRAY SCALE DOCUMENTS**
- ☒ **LINES OR MARKS ON ORIGINAL DOCUMENT**
- ☐ **REFERENCE(S) OR EXHIBIT(S) SUBMITTED ARE POOR QUALITY**
- ☐ **OTHER: _____**

IMAGES ARE BEST AVAILABLE COPY.

As rescanning these documents will not correct the image problems checked, please do not report these problems to the IFW Image Problem Mailbox.